

## HHPL DPC 1 DAMP PROOF COATING

### ***A SOLVENT BASED LIQUID APPLIED BITUMINOUS WATERPROOFING MEMBRANE***

#### Description

HHPL DPC 1 Damp Proof Coating is a high performance single compound solvent based bituminous liquid state membrane specially developed for indoor/ outdoor damp proof waterproofing applications.

#### Product Uses

- **Bituminous Waterproofing Coating**
- **Water Vapour Barrier**

#### Physical and Chemical Properties

Solid content	>55 ± 1 %
Specific Gravity	0.98
Viscosity	25 – 125 Sec: Say bolt Furol @ 25oC
Working Temperature Range	20oC to 72oC

#### Instruction for Application

##### Preparation

All surfaces to be waterproofed should be sound, clean and dry. Concrete surfaces should have a light steel-trowel smooth finish and followed by a fine hair-broom or equivalent finish which is dry and free of dust, oil and other contaminants. All high spots should be removed. Moss and lichen must be removed physically followed by treatment with fungicidal wash to kill any spores and inhibit further growth. After treatment wash down thoroughly with clean water and allow drying. All metal surfaces should be made clean of paints, oils, rust and other contaminants. Abrade to expose bright metal then wipe clean with Solvent (Thinner AAA) prior to priming.

#### Application

HHPL DPC1 Damp Proof Coating should be applied by brush or roller (two coat application for standard grade on vertical surfaces). Allow 8 hours between coats and apply each coat at right angle to the previous coat.

#### Curing and Protection

HHPL DPC1 Damp Proof Coating membrane must be cured for a minimum of 24hours @ 25°C before placing protection. Where damage to the membrane is possible (by traffic or backfilling, etc.) it should be protected by a cementitious screed or protection boards.

#### Supply and Coverage

Supply                      4 Liter

Coverage                    2.5 m2 per coat

# MATERIAL SAFETY DATA SHEET



## HHPL DPC 1 DAMP PROOF COATING

### **A SOLVENT BASED LIQUID APPLIED BITUMINOUS WATERPROOFING MEMBRANE**

#### Product Information and Company Identification

Product Identification	DPC1 Damp Proof Coating
Product Use	Bituminous Waterproofing Membrane
Company Identification	HENDRICKS Holdings Private Limited 114/2, Thumbowila, Piliyandala Sri Lanka
Telephone	(+94) 115 741 133
Fax	(+94) 112 614 727
Website	<a href="http://www.hendricks.lk">www.hendricks.lk</a>
Email	<a href="mailto:info@hendricks.lk">info@hendricks.lk</a>
Date of Issue	July 2016

#### First Aid Measures

##### Swallowed

Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

##### Eye

If this product comes in contact with eyes, Wash out immediately with cold water immediately for at least 15 minutes. If irritation continues, seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.



##### Skin

If skin or hair contact occurs, Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.



##### Inhaled

If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.



##### Advice to Doctor

No specific antidote. Treat symptomatically.

## Accidental Release Measures

**Spills** Confine the spill to a small area. Use a commercial kit or absorbent material to absorb spilled materials. Place spilled material in a container for disposal.

## Handling, Storage and Shelf Life

**Handling** Keep out of reach of children. Harmful if swallowed. Causes eye irritation and skin sensitivity. Avoid eye, skin & clothing contact. After work, remove protective clothing and equipment, wash hands before eating, drinking, Smoking or using toilet. Wash clothing after use.

**Storage** Store in tightly closed original container in a cool, dry, well-ventilated and secure area when not in use. Do not store with food, feedstuffs, Seed or fertilizers. Once open, use within one month and make sure to keep it sealed within the original container.

## Shelf life

**DPC1 Damp Proof Coating** has a shelf life of 24 months if kept below 25°C in the original, unopened condition.

## Disposal Considerations

**Disposal Method** Triple rinse empty containers before disposal. Do not burn empty containers that have not been rinsed. Burn in an appropriate incinerator if circumstances such as wind direction permit. Otherwise crush or puncture and bury in a suitably approved landfill. Do not dispose of this product down drains or sewers. Follow all local, regional and national laws and regulations regarding hazardous waste disposal.

## Transport Information

**Transport limitations** Do not carry this product on a public passenger vehicle. No limitation on non-passenger vehicles. Must be transported in original sealed and labeled container.

**Disclaimer:** *The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion; however there may be inadvertent and occasional errors which may have slipped from our notice. **Hendricks Holdings (Private) Limited** does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. **Hendricks Holdings (Private) Limited** accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.*

*“At Hendricks we do care about nature. Therefore Hendricks **Green Earth** Program plants a tree for every purchase you make.....”*

